

07/06/2004 12:49 813-806-1988

DTI

PAGE 02

✓ 07-06-04

60998 - 0009
- 0129
60999 - 0002

DIAMOND TECH INTERNATIONAL MATERIAL SAFETY DATA SHEET

SECTION I

PRODUCT: MOSAIC STONE CEMENT
DATE ISSUED: AUGUST 9, 1998
CHEMICAL FAMILY: Calcium Sulfate Hemihydrate

PRODUCT NO: 20068

SECTION II HAZARDOUS INGREDIENTS

MATERIAL:	8	TLV:
Portland Cement	2	10 mg/M3*

*ACGIH (1981) - 5 mg/M3 respirable

SECTION III PHYSICAL DATA

SOLUBILITY IN WATER: 0.2%
SPECIFIC GRAVITY (H2O = 1): 2.7
APPEARANCE AND ODOR: Odorless white powder
HARDENING TIME: Less than 20 minutes

SECTION IV FIRE AND EXPLOSION HAZARD DATA

FLASH POINT (METHOD USED): Not applicable
EXTINGUISHING MEDIA: Not combustible
SPECIAL FIRE FIGHTING PROCEDURES: Not combustible
UNUSUAL FIRE AND EXPLOSION HAZARDS: None

SECTION V HEALTH HAZARD DATA

EFFECTS OF OVEREXPOSURE: May cause irritation of eyes and skin. May develop sufficient heat to cause burns if a large mass, such as a cast of a hand or arm, is kept in contact with skin while hardening. INHALATION: Dust is considered a nuisance dust.
EMERGENCY AND FIRST AID PROCEDURES:
EYES: Flush immediately for 15 minutes with water.
SKIN: Remove from skin by washing. If irritation continues, see physician.
INGESTION: Gypsum cement hardens when wetted and if ingested may result in obstruction. See Section III for Hardening Time. See physician.

07/06/2004 12:49 813-806-1988

DTI

PAGE 03

PAGE 2

PRODUCT NO: 20068

SECTION VI
REACTIVITY DATA

STABILITY: Stable
HAZARDOUS POLYMERIZATION: Will not occur.

SECTION VII
SPILL OR LEAK PROCEDURES

STEPS TO BE TAKEN IN CASE MATERIAL IS RELEASED OR SPILLED:
Sweep up. Avoid creating excessive dust. Slurry may plug drain.
WASTE DISPOSAL METHOD: In accordance with local, state and federal regulations.

SECTION VIII
SPECIAL PROTECTION INFORMATION

RESPIRATORY PROTECTION: NIOSH approved nuisance dust respirator if above TLV.
VENTILATION: General mechanical. Local exhaust if above TLV.
PROTECTIVE EQUIPMENT: Dust goggles if dust is annoying or safety glasses. Gloves if dust or slurry is irritating.

SECTION IX
SPECIAL PRECAUTIONS

PRECAUTIONS TO BE TAKEN IN HANDLING AND STORING: Dew point conditions or other conditions causing presence of liquid water during storage will harden gypsum cement.